



Technical Datasheet: EVA 1328

Product Description:

HANWHA EVA 1328 is manufactured by Dow autoclave high pressure process and designed for variety of foam molding application such as shoes and sandals etc. EVA 1328 is well known for its excellent processability and high quality assurance.

Applications:

Shoes and sandals etc.

Typical data:

PROPERTY	TEST METHOD	UNIT	VALUE
Melt Index	ASTM D 1238	g/10min	2.5
VA Content	HCC Method(3)	wt%	28.0
Density	ASTM D 1505	g/cm ³	0.950
Vicat Softening Point	ASTM D 1525	°C	44
Melting Point	ASTM D 3417	°C	71
Tensile Strength at Break	ASTM D 638	Kg/cm ²	141
Elongation at Break	ASTM D 638	%	900
Brittleness Temperature, F _b	ASTM D746	°C	<-76
Hardness	ASTM D 2240	Shore A/D	79/26

* Typical values not to be construed as specifications.