

Technical Datasheet: EVA VA800

Product Description:

SEETEC VA800 resin is produced by ExxonMobil Chemical's autoclave process technology. SEETEC VA800 resin, with 28% VA content, is an excellent raw material in the application of hot melt adhesives

Applications:

- Adhesives
- Automotive
- Coating

Typical data:

PROPERTY	TEST METHOD	UNIT	VALUE
Density	ASTM D 1505	g/cm3	0.950
Melt Mass-Flow Rate(MFR)(190°C/2.16kg)	ASTM D 1238	g/10min	20
Vinyl Acetate Content	-	wt%	28.0
Rockwell Hardness	ASTM D 785	-	25
Vicat Softening Temperature	ASTM D1525	°C	<40.0
Melting Temperature	-	°C	69.0

^{*} Typical values not to be construed as specifications.

Email: info@anahitaholding.com Web: www.anahitaholding.com