



## Technical Datasheet: PA TW341

### Product Description:

PA TW341 is a heat Stabilized, wear and friction modified PA46.

### Applications:

Advanced engineering application such as auto parts.

### Typical data:

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE
Molding shrinkage (parallel)	ISO 294-4	%	~2 / *
Molding shrinkage (normal)	ISO 294-4	%	2 / *
Tensile modulus	ISO 527-1/-2	MPa	3300
Tensile modulus (120°C)	ISO 527-1/-2	MPa	800
Tensile modulus (160°C)	ISO 527-1/-2	MPa	650
Tensile modulus (180°C)	ISO 527-1/-2	MPa	600
Tensile modulus (200°C)	ISO 527-1/-2	MPa	500
Yield stress	ISO 527-1/-2	MPa	100 / 55
Yield stress(120°C)	ISO 527-1/-2	MPa	50
Yield stress(160°C)	ISO 527-1/-2	MPa	40
Yield stress(180°C)	ISO 527-1/-2	MPa	35
Yield stress(200°C)	ISO 527-1/-2	MPa	30
Nominal strain at break	ISO 527-1/-2	%	40/ >50
Nominal strain at break(120°C)	ISO 527-1/-2	%	>50
Nominal strain at break(160°C)	ISO 527-1/-2	%	>50
Nominal strain at break(180°C)	ISO 527-1/-2	%	>50
Nominal strain at break(200°C)	ISO 527-1/-2	%	>50
Flexural modulus	ISO 178	MPa	3000 / 900
Flexural modulus(120°C)	ISO 178	MPa	800
Flexural modulus(160°C)	ISO 178	MPa	600
Charpy impact strength (+23°C)	ISO 179/1eU	kJ/m <sup>2</sup>	N/N
Charpy impact strength (-30°C)	ISO 179/1eU	kJ/m <sup>2</sup>	N/N
Charpy notched impact strength (+23°C)	ISO 179/1eA	kJ/m <sup>2</sup>	10/ 35
Charpy notched impact strength (-30°C)	ISO 179/1eA	kJ/m <sup>2</sup>	4/4
Izod notched impact strength (+23°C)	ISO 180/1A	kJ/m <sup>2</sup>	10/35
Izod notched impact strength (-40°C)	ISO 180/1A	kJ/m <sup>2</sup>	4/4
Melting temperature (10°C/min)	ISO 11357-1/-3	°C	295 / *
Temp. of deflection under load (1.80 MPa)	ISO 75-1/-2	°C	190 / *

# Anahita Holding

*We win first, then start the challenge!*

Temp. of deflection under load (0.45 MPa)	ISO 75-1/-2	°C	280/*
Coeff. of linear therm. expansion (parallel)	ISO 11359-1/-2	E-4/°C	0.85/ *
Coeff. of linear therm. expansion (normal)	ISO 11359-1/-2	E-4/°C	1.1 / *
Burning Behav. at 1.5 mm nom. thickn.	IEC 60695-11-10	class	V-2 / *
Thickness tested	IEC 60695-11-10	mm	1.5 / *
UL recognition	-	-	Yes / *
Burning Behav. at thickness h	IEC 60695-11-10	class	V-2 / *
Thickness tested	IEC 60695-11-10	mm	0.75 / *
UL recognition	-	-	Yes / *
Relative Temperature Index – electrical	UL746B	°C	150
RTI electrical(Thickness (1) tested)	UL746B	mm	0.75
Thermal Index 5000 hrs	IEC 60216/ISO 527-1/-2	°C	152
Volume resistivity	IEC 60093	Ohm*m	1E13 / 1E7
Electric strength	IEC 60243-1	kV/mm	25/15
Comparative tracking index	IEC 60112	-	400 /-
Relative permittivity (1Hz)	IEC 60250	-	3.6/4.5
Humidity absorption	Sim. to ISO 62	%	3.7/ *
Density	ISO 1183	kg/m3	1180 / -

\* Typical values not to be construed as specifications.